



# micromod Partikeltechnologie GmbH

Friedrich-Barnewitz-Str. 4  
D-18119 Rostock  
Germany

Phone: +49 381 / 54 34 56 10  
Fax: +49 381 / 54 34 56 20  
E-mail Address: info@micromod.de

## Technical Data Sheet

---

Product-No.:	<b>09-55-502</b>
Product-Name:	<b>nanomag® -D</b>
Surface:	<b>PEG-NH2</b>
Size:	<b>500 nm</b>
Solid content:	<b>10 mg/ml</b>
Quantity:	<b>10 ml</b>
Composition:	dextran iron oxide composite particles
Polydispersity Index:	< 0.2
Shape:	cluster-typed
Density:	3.0 g/ccm
Magnetization:	47 emu/g iron (H =1000 Oe)
Saturation Magnetization:	>70 emu/g iron (H > 10.000 Oe)
Coercive Field Hc:	0.677 kA/m
Stable in:	aqueous buffers pH > 4
Not stable in:	organic solvents, acidic solutions pH < 4
Product Form:	aqueous suspension
Particles per ml:	6.1*10E10
Particles per mg:	6.1*10E9
Additional Remarks:	Storage at 2 - 8°C for 6 months