

# micromod Partikeltechnologie GmbH

Friedrich-Barnewitz-Str. 4  
D-18119 Rostock  
Germany

fon: +49 381 / 54 34 56 10  
fax: +49 381 / 54 34 56 20  
e-mail: info@micromod.de



## Technical Datasheet

---

Product-No.:	<b>08-02-703</b>
Product-Name:	<b>micromer® -M</b>
surface:	<b>COOH</b>
size:	<b>7 µm</b>
solid content:	<b>50 mg/ml</b>
quantity:	<b>10 ml</b>
Shape:	spherical
Density:	1.3 g/ccm
Magnetization:	3.0 emu/g particles (H =1000 Oe)
Saturation magnetization:	> 3.6 emu/g particles (H > 7.000 Oe)
Stable in:	aqueous buffers, methanol, ethanol, DMSO
Not stable in:	halogenated hydrocarbons, toluene, strong acidic solutions, eg 10% HCl
Product form:	aqueous suspension
Particles per ml:	2.1*10E8
Particles per mg:	4.3*10E6
Charge density:	6 µmol/g
Protein binding capacity:	350 ng albumin (BSA) / mg particle