

# micromod Partikeltechnologie GmbH

Friedrich-Barnewitz-Str. 4  
D-18119 Rostock  
Germany

fon: +49 381 / 54 34 56 10  
fax: +49 381 / 54 34 56 20  
e-mail: info@micromod.de



## Technical Datasheet

---

Product-No.:	<b>43-02-153</b>
Product-Name:	<b>sicastar®</b>
surface:	<b>COOH</b>
size:	<b>1.5 µm</b>
solid content:	<b>50 mg/ml</b>
quantity:	<b>10 ml</b>
Composition:	amorphous silica particles
Polydispersity index:	< 0.2
Shape:	spherical
Density:	2.0 g/ccm
Porosity:	nonporous
Stable in:	aqueous buffers, organic solvents
Not stable in:	hydrofluoric acid, strong basic media, e.g. 6 M NaOH
Product form:	aqueous suspension
Particles per ml:	1.4*10E10
Particles per mg:	2.8*10E8
Surface charge density:	2 µmol/g
Protein binding capacity:	2.2 µg albumin (BSA) / mg particle
Additional remarks:	Storage at room temperature.