

micromod Partikeltechnologie GmbH

Friedrich-Barnewitz-Str. 4
D-18119 Rostock
Germany

fon: +49 381 / 54 34 56 10
fax: +49 381 / 54 34 56 20
e-mail: info@micromod.de



Technical Datasheet

Product-No.:	43-17-502
Product-Name:	sicastar®
surface:	TMS
size:	500 nm
quantity:	0.5 g
Composition:	amorphous silica particles
Polydispersity index:	< 0.2
Shape:	spherical
Density:	2.0 g/ccm
Porosity:	nonporous
Stable in:	aqueous buffers, organic solvents
Not stable in:	hydrofluoric acid, strong basic media, e.g. 6 M NaOH
Product form:	dry powder
Particles per mg:	7.6*10E10
Additional remarks:	Ultrasound treatment is recommended for resuspension. Storage at room temperature.