

# micromod Partikeltechnologie GmbH

Friedrich-Barnewitz-Str. 4  
D-18119 Rostock  
Germany

fon: +49 381 / 54 34 56 10  
fax: +49 381 / 54 34 56 20  
e-mail: info@micromod.de



## Technical Datasheet

---

Product-No.:	<b>43-20-104</b>
Product-Name:	<b>sicastar®</b>
surface:	<b>proteinA</b>
size:	<b>10 µm</b>
solid content:	<b>25 mg/ml</b>
quantity:	<b>1 ml</b>
Composition:	amorphous silica particles
Standard deviation:	< 2.5 µm
Shape:	spherical with irregularities
Density:	1.8 g/ccm
Porosity:	porous
Stable in:	aqueous buffers
Not stable in:	hydrofluoric acid, strong basic media, e.g. 6 M NaOH
Product form:	suspension in PBS buffer (pH = 7.4), stabilized in 0.02 % sodium azide
Particles per ml:	2.7*10E7
Particles per mg:	1.1*10E6
Protein binding capacity:	200 ng protein A / mg particle (67 ng protein A / cm <sup>2</sup> )
Additional remarks:	Storage at 2 - 8°C for 3 months